

Influence of $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ phosphor's concentration on optical properties of the 5600K RP-WLEDs

Phu Tran Tin¹, Minh Tran², and Tran Thanh Trang³

¹Faculty of Electronics Technology, Industrial University of Ho Chi Minh City, Vietnam

²Optoelectronics Research Group, Faculty of Electrical and Electronics Engineering,
Ton Duc Thang University, Vietnam

³National Key Laboratory of Digital Control and System Engineering, Vietnam

Article Info

Article history:

Received May 10, 2019

Revised Oct 23, 2019

Accepted Oct 30, 2019

Keywords:

CQS

CRI

Optical properties

Phosphor

RP-WLEDs

ABSTRACT

In this paper, we propose $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ Phosphor as a new material solution for improving the optical properties in terms of CRI, CQS, D-CCT, LO of the 5600K remote-packaging white LEDs (RP-WLEDs). In the first stage, we built and investigated the 5600K RP-WLEDs by adding the red phosphor to the phosphor layer. Then, the scattering processes inside the phosphor layer are investigated by Mat Lab software. From the research results, we discovered that the concentration of the adding phosphor significantly improved the optical properties of the 5600K RP-WLEDs. All the results are convinced by Light Tools and Mat Lab software.

Copyright © 2020 Institute of Advanced Engineering and Science.
All rights reserved.

Corresponding Author:

Minh Tran,
Optoelectronics Research Group,
Faculty of Electrical and Electronics Engineering,
Ton Duc Thang University, Ho Chi Minh City, Vietnam.
Email: tranhoangquangminh@tdtu.edu.vn

1. INTRODUCTION

In comparison with incandescent and fluorescent lamps, the InGaN-based white-light-emitting diodes (LEDs) have many advantages in energy efficiency, long lifetime, compactness, and environment-friendly and designable features. Phosphor converted LEDs (pcLED), which combines a blue LED chip and the yellow emitting phosphor, is the most common way to conduct the white light emission through LEDs packaging [1-5]. Thickness and concentration of phosphor are considered as the main factors in the white LEDs packaging because the luminous flux and color of LEDs are adjusted mainly through changing the phosphor thickness and concentration after the phosphor converters are chosen. The influence of phosphor thickness and concentration on LEDs luminous flux and CCT is studied in [6, 7] by experiment. Authors in [8] investigated the effects of phosphor thickness, concentration, and size on the spatial color distribution of white LEDs. In [9-12], the effect of phosphor location on the spatial color distribution was investigated. Moreover, some researchers were concentrated on enhancing the optical performance of multi-chip white LEDs (MCW-LEDs) by adding green or red phosphor into the phosphor layer [13-17].

The optical properties of the 5600K RP-WLEDs is considered as a novel method. From the research, results we can state that the CCT Deviation (D-CCT), CRI, CQS, and lumen output may be significantly increased by varying the concentration of $\alpha \text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ phosphor particles from 10% to 30%. In this paper, we focus on the main contributions as follows:

- We conduct the RP-WLEDs model by Light Tools software.
- The scattering process in the phosphor layer of the RP-WLEDs is investigated with Mat Lab software.

- c. The influence of the red phosphor on the optical properties in terms of CRI, CQS, D-CCT, and LO is analyzed.

The structure of the rest of the paper can be drawn as follows. The research method is proposed in the second section. Section 3 presents the research results and makes some discussions. Some conclusions are drawn in the last section.

2. RESEARCH METHOD

In this section, the 5600K RP-WLEDs are employed. Figure 1(a) presents a real WLEDs package. Based on this package, the remote phosphor compound should be simulated by the Light Tools software, as shown in Figure 1(b). In this model, RP-WLEDs have been configured as in previous studies. The main parameters of the 5600K RP-WLEDs can be conducted as in [13].




Figure 1. (a) The real white LED package; (b) Physical model of the RP-WLEDs package.

3. RESULTS AND ANALYSIS

In this simulation, the concentration of $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ should be varied continuously from 10% to 30% for selecting a proper concentration. The optical properties of $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ particles are configured by using the Light Tools software based on Mie-theory as in [13, 18-25]. The scattering coefficient $\mu_{\text{scattering}}(\lambda)$, anisotropy factor $g(\lambda)$, and reduced scattering coefficient $\delta_{\text{sca}}(\lambda)$ can be formulated as:

$$\mu_{\text{scattering}}(\lambda) = \int N(r)C_{\text{scattering}}(\lambda, r)dr, \quad (1)$$

$$g(\lambda) = 2\pi \int_{-1}^1 p(\theta, \lambda, r)f(r) \cos \theta d(\cos \theta)dr, \quad (2)$$

$$\delta_{\text{scattering}} = \mu_{\text{scattering}}(1 - g). \quad (3)$$

In these equations, r is the radius of particles (μm), $C_{\text{scattering}}$ is the scattering cross-sections (mm^2), λ is the light wavelength (nm), $N(r)$ indicates the distribution density of particles (mm^{-3}), θ is the scattering angle, $p(\theta, \lambda, r)$ is the phase function, and $f(r)$ is the size distribution function of $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ particles.

The scattering coefficients increase significantly with the rising $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ concentration from 0% to 30%, as plotted in Figure 2. The scattering coefficients at 453 nm get the highest values and the lowest ones at 555 nm. Figure 3 shows the anisotropy factors of $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ particles at the wavelengths of 453 nm, 555 nm, and 680 nm, respectively. It is observed from the results that the anisotropy factor values at 680 nm are higher than at 555 nm. However, it is at 453 nm that the maximum anisotropy factor value is obtained. From simulation results, the anisotropy factors have a slight deviation approximately between 0.978 and 0.982. The concentration of $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ particles is varied from 0% to 30%, continuously. The reduced scattering coefficients of $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ at 453 nm, 555 nm, and 680 nm wavelengths grow with $\text{Ca}[\text{Mg}_3\text{SiN}_4]\text{Ce}^{3+}$ concentration, as shown in Figure 4. The deviations of the reduced scattering coefficients among three wavelengths are the same values [13, 18-22].




Figure 2. Scattering coefficients




Figure 3. Anisotropy scattering




Figure 4. Reduced scattering coefficients

From Figure 5, we can state that the CRI rises from 64 to 74, while the concentration of the phosphor varies from 10 to 30%. In the same way, the CQS increases from 63.5 to 69.5 while the concentration of the phosphor varies from 10 to 30% are plotted in Figure 6. From these results, we can say that the concentration of the red phosphor significantly influences on the color quality of the 5600K RP-WLEDs. Furthermore, the influence of the red phosphor concentration on the LO and D-CCT of the 5600K RP-WLEDs is illustrated in Figure 7 and 8. As shown in Figure 7, LO increases with 10% to 25% concentration of the red phosphor and then has a huge decrease with 25% to 30% concentration of the red phosphor. Moreover, D-CCT has a slight decrease when the concentration of the red phosphor varies from 10% to 30%.




Figure 5. CRI




Figure 6. CQS




Figure 7. Luminous flux




Figure 8. D-CCT

4. CONCLUSION

In this paper, we propose $\text{Ca}[\text{Mg}_3\text{Si}_4\text{N}_4]\text{Ce}^{3+}$ Phosphor as a novel recommendation for improving the optical properties in terms of CRI, CQS, D-CCT, and LO of the 5600K RP-WLEDs. From the research results, we discovered that the concentration of the adding phosphor significantly improved the optical properties of the 5600K RP-WLEDs. All the results are convinced by Light Tools and Mat Lab software. The CRI can be increased from 74 to 85, and CQS from 64 to 70, respectively. This research can provide a novel recommendation for improving the optical properties of the RP-WLEDs.

ACKNOWLEDGEMENTS

This research was supported by National Key Laboratory of Digital Control and System Engineering (DCSELAB), HCMUT, VNU-HCM, Vietnam.

REFERENCES

- [1] S. Liu and X. Luo, "Design of LED Packaging Applications," *LED Packaging for Lighting Applications: Design, Manufacturing and Testing*, pp. 215–315, 2011.
- [2] E. Gibney, "Nobel for Blue LED that Revolutionized Lighting." *Nature*, vol. 514, pp. 152–153, 2014.
- [3] H. Winkler, Q. Trinh, P. Bodrogi, and T. Q. Khanh, "LED Lighting: Technology and Perception," *Weinheim: Wiley-VCH*, 2015.
- [4] X. Luo, R. Hu, S. Liu, and K. Wang, "Heat and Fluid Flow in High-Power LED Packaging and Applications," *Progress in Energy and Combustion Science*, vol. 56, pp. 1–32, 2016.
- [5] R. Hu, X. Luo, and S. Liu, "Effect of the Amount of Phosphor Silicone Gel on Optical Property of White Light-Emitting Diodes Packaging," *2011 12th International Conference on Electronic Packaging Technology and High Density Packaging*, pp. 1081-1084, 2011.
- [6] N. T. Tran and F. G. Shi, "Studies of Phosphor Concentration and Thickness for Phosphor-Based White Light-Emitting-Diodes," *Journal of Lightwave Technology*, vol. 26 (21), pp. 3556–3559, 2008.
- [7] Y. Shuai, Y. He, N. T. Tran, and F. G. Shi, "Angular CCT uniformity of phosphor-converted white LEDs: effects of phosphor materials and packaging structures," *IEEE Photonics Technology Letters*, vol. 23(3), pp. 137–139, 2011.
- [8] C. Sommer, F-P. Wenzl, P. Hartmann, P. Pachler, M. Schweighart, S. Tasch, and G. Leising, "Tailoring of the Color Conversion Elements in Phosphor-Converted High-Power LEDs by Optical Simulations." *IEEE Photonics Technology Letters*, vol. 20(9), pp. 739–741, 2008.
- [9] S. Li, K. Wang, F. Chen, S. Zhao, Z. Zhao, and S. Liu, "Angular Color Uniformity Enhancement of Phosphor Converted White LEDs Integrated with Compact Modified Freeform TIR Components." *2012 13th International Conference on Electronic Packaging Technology & High Density Packaging*, 2012.
- [10] Z. Liu, S. Liu, K. Wang, and X. Luo, "Analysis of Factors Affecting Color Distribution of White LEDs," *2008 International Conference on Electronic Packaging Technology & High Density Packaging*, 2008.
- [11] Z. Liu, S. Liu, K. Wang, and X. Luo, "Optical Analysis of Color Distribution in White LEDs with Various Packaging Methods," *IEEE Photonics Technology Letters*, vol. 20(24), pp. 2027–2029, 2008.
- [12] Z. Liu, S. Liu, K. Wang, and X. Luo, "Effects of Phosphor's Location on LED Packaging Performance," *2008 International Conference on Electronic Packaging Technology & High Density Packaging*, 2008.
- [13] P. T. Tin, N. H. K. Nhan, and T. H. Q. Minh, "Using Green Emitting Phosphor for Improving Lighting Performance of In-cup Package White LED Lamps," *International Journal of Power Electronics and Drive Systems (IJPEDES)*, vol. 8, no. 1, pp. 125, March 2017.

- [14] A. A. Ali, K.t. Al-Rasoul, and I. M. Ibrahim, "Influence of Doping and Annealing on Structural, Optical and Electrical Properties Amorphous ZnO Thin Films Prepared by PLD," *Indonesian Journal of Electrical Engineering and Informatics (IJEI)*, vol. 3, no. 1, March, 2015.
- [15] K. S. Chia and Y. P. Tan, "Design and Development of a Shortwave near Infrared Spectroscopy using NIR LEDs and Regression Model," *International Journal of Electrical and Computer Engineering (IJECE)*, vol. 7, no. 6, pp. 3070-3075, Dec., 2017.
- [16] M. Quinten, "Beyond Mie's Theory II-The Generalized Mie Theory," *Optical Properties of Nanoparticle Systems: Mie and Beyond*, 317–339, 2011.
- [17] J. R. Frisvad, N. J. Christensen, and H. W. Jensen, "Predicting the Appearance of Materials using Lorenz–Mie Theory," *The Mie Theory Springer Series in Optical Sciences*, 101–133, 2012.
- [18] D. Mackowski, "The Extension of Mie Theory to Multiple Spheres." *The Mie Theory Springer Series in Optical Sciences*, 223–256, 2012.
- [19] T. Wriedt, "Mie Theory: A Review," *The Mie Theory Springer Series in Optical Sciences*, 53–71, 2012.
- [20] M. I. Mishchenko, L. D. Travis, and A. A. Lacis, "Scattering, Absorption, and Emission of Light by Small Particles, Cambridge:Cambridge University Press, 2012..
- [21] J. Zhong, M. Xie, Z. Ou, R. Zhang, M. Huang, and F. Zhao. "Mie Theory Simulation of the Effect on Light Extraction by 2-D Nanostructure Fabrication." *2011 Symposium on Photonics and Optoelectronics (SOPO)*, 2011.
- [22] T. H. Q. Minh, N. H. K. Nhan, N. D Q Anh, and H.-Yi Lee. "Red-Emitting α -SrO·3B₂O₃:Sm²⁺ Phosphor: an Innovative Application for Increasing Color Quality and Luminous Flux of Remote Phosphor White LEDs." *Journal of the Chinese Institute of Engineers* 40 (4): 313–317.
- [23] N. D. Q. Anh, H-Y. Lee, T. T. Phuong, N. H. K. Nhan, T. H. Q. Minh, and T. H. Ly, "Y₂O₃:Eu³⁺ Phosphor: a Novel Solution for an Increase in Color Rendering Index of Multi-Chip White LED Packages." *Journal of the Chinese Institute of Engineers*, vol. 40(3), pp.: 228–234, 2017.
- [24] h, Nguyen Doan Quoc, and H.-Yi Lee, "Improving the Angular Color Uniformity and the Lumen Output for Multi-Chip White LED Lamps by Green Ce_{0.67}Tb_{0.33}MgAl₁₁O₁₉:Ce, Tb Phosphor," *Journal of the Chinese Institute of Engineers* vol. 39 (7), 871–875, 2016.
- [25] X. Lu⁰, and R Hu., "Chip packaging: Encapsulation of Nitride LEDs. *Nitride Semiconductor Light-Emitting Diodes (LEDs)*, 441-481, 2014.